

Technical Datasheet		Kotar polypropylene fabric with print		
PP - coating				
Technical data	Test	Unit	Setpoint	tolerance
Total weight	EN ISO 2286-2	g/m ²	72	(+/-)5 %
Weight coating	EN ISO 2286-2	g/m ²	20	(+/-)5 %
Weight fabric	EN ISO 2286-2	g/m ²	52	(+/-)5 %
Tensile strength (MD)	EN ISO 527-3	N/5cm	668	(+/-)10 %
Tensile strength (CD)	EN ISO 527-3	N/5cm	590	(+/-)10 %
Elongation (MD)	EN ISO 527-3	%	20	(+/-)10 %
Elongation (CD)	EN ISO 527-3	%	20	(+/-)10 %
Shrinkage 2h - 50°C		%	1	1%>
Shrinkage 2h - 60°C		%	1	1%>
Shrinkage 2h - 70°C		%	1	1%>
Corona pretreatment		mN/m	40	-2/2
Warp tape		mm	3	(+/-)0,15 mm
Weft tape		mm	4	(+/-) 0,15 mm
Roll make-up				
Core	76 mm			
Standard widths	1030 mm			
Packaging	pallet			
Created: 27.04.2022				